



## PRODUCT DESCRIPTION

VpCI-388 is a temporary removable coating that leaves a firm, dry film. VpCI-388 can be easily removed by alkaline cleaners such as Cortec® VpCI-414. VpCI-388 is an excellent choice for long-term indoor corrosion protection (up to three years\*) or medium to short-term outdoor conditions. The recommended film thickness is 2 mils (50 microns).

\*Depends on conditions and/or film thickness

## FEATURES

- Available in custom colors
- Non-tacky and removable film
- Dries to a clear matte finish
- Environmentally friendly and disposable
- NSN 8030-01-481-8898

## TYPICAL APPLICATIONS

- Transit protection of heavy equipment
- OEM
- Parts shipping
- Additional protection to painted surfaces

## TYPICAL PROPERTIES

Appearance	Off-white viscous liquid
Film Type	Firm
Non-volatile Content	32-40%
pH	8.7-9.2 (Neat)
Coverage	596-680 ft <sup>2</sup> /gal at 1 mil (15-17 m <sup>2</sup> /l at 25 microns)
Density	8.2-8.4 lb/gal (0.98-1.01 kg/l)
Viscosity	8,000-15,000 cps
VOC (regulatory)	0.4-0.5 lb/gal (48-60 g/l)
VOC (regular)	0.2-0.3 lb/gal (24-36 g/l)
Dry to Touch Time	5-30 minutes*
Dry to Cure Time	4-6 hours*
Shelf Life	12 months at 75°F (24°C)
Salt Spray Resistance	100 hours
Humidity Resistance	150 hours

\*Depends on dilution

**Note: Coating dry time is affected by temperature, air-flow and humidity.**

## PACKAGING AND STORAGE

VpCI-388 is available in 5 gallon (19 liter) pails, 55 gallon (208 liter) metal drums, liquid totes, and bulk. Do not allow product to freeze.

